

MARKLON POLYGLASS® Polycarbonate Hollow Sheet Quality Certificate

Purchaser :
Invoice No & Date : **S A M P L E**
Product :
Project :

This is to certify that we warranty Marklon Polyglass® Polycarbonate Hollow Sheet with *10 years limited warranty from quality extreme changes such as colour deterioration.

*Sheet Replacement Cost Calculation : $(UM \div 120) \times OPP$

UM = Unutilized Months (Balance from 120 months)

OPP = Original Purchase Price (paid by customer in respect of the sale)

Complaint has to be made within 14 days in writing to our dealer, agent or Marklon Industries Sdn Bhd for investigation.

Sheet has to be changed within 45 days if the result proven to be manufacturer defect.

This warranty will become valid only if : -

- i) The end user gives written notice, presenting the invoice and submits sample of the defective sheet within 14 days after the defect was detected.
- ii) The end user has allowed an inspection by our dealer, agent or Marklon Industries Sdn Bhd representatives.
- iii) The sheets were used under normal conditions.
- iv) The sheets defectives were proof to be manufacturer's defect.

The extent of Marklon Polyglass® Polycarbonate Hollow Sheet warranty obligation is restricted to the following : -

- i) This warranty does not include sheet defectives caused by hailstorm / natural disaster.
- ii) This warranty does not include sheet defectives which may result from improper storage, neglect or misapplication of the product.
- iii) This warranty does not apply to Marklon Polyglass® Polycarbonate Hollow Sheet that has been thermoformed or molded.
- iv) This warranty does not include any direct or indirect expenses or losses incurred from sheet defectives due to non-compliance by any user with the following provisions : -
 - a) Marklon Polyglass® Polycarbonate Hollow Sheet must be protect against exposure to abrasive chemical such as cement, paint, petrol, etc
 - b) Must use santoprene gasket in direct contact with Marklon Polyglass® Polycarbonate Hollow Sheet.
 - c) Avoid scratching and denting on Marklon Polyglass® Polycarbonate Hollow Sheet surfaces.
 - d) Do not use incompatible connecting, fixing and tightening elements to install Marklon Polyglass® Polycarbonate Hollow Sheet.
 - e) Only apply neutral sealant or compatible adhesives.
 - f) When cutting Marklon Polyglass® Polycarbonate Hollow Sheet, heat and compression are to be avoided.
 - g) The U.V. protected surface of Marklon Polyglass® Polycarbonate Hollow Sheet has to be faced towards the sunlight (PE film masking printed with Marklon Polyglass® logo)
 - h) The bending radius may not be less than 175 times of the Marklon Polyglass® Polycarbonate Hollow Sheet thickness.