REPORT NO : 2022CE1302-S1 PAGE : 3 OF 6

This Test Report refers only to samples submitted by the applicant to SIRIM QAS International Sdn. Bhd. and tested by SIRIM QAS International Sdn. Bhd. This Test Report shall not be reproduced, except in full and shall not be used for any purpose by any means or forms (including but not limited to advertising purposes) without written approval from the Head of Quality, Occupational Safety and Health & Environment (QOSHE), SIRIM QAS International Sdn. Bhd. Please refer to the last page of this Test Report for Conditions Relating to the Use of Test Report.

## Results

Product : POLYCARBONATE SHEET
Brand : MARKLON POLYGLASS
Model : MK95 Clear Plane (6 MM)

**Description: POLYCARBONATE SOLID SHEET** 

NO.		TEST	RESULT	TEST METHOD
1	Izod Noto	Impact Strength -	(110 ± 1*) J/m	ASTM D256  Test parameters:  • Method A  • Pendulum: 2.75 Joule  • Velocity: 3.46 m/s  • No. of specimens tested per sample: 15 pieces  Test date: 25 May 2022
2	Den	sity	(1.195 ± 0.0003*) g/cm <sup>3</sup>	ASTM D792  Test parameters:  • Method A - Immersion in water
3	Spe	cific Gravity**	1.198	<ul> <li>Test temperature: 24.4°C</li> <li>Number of specimens tested: 5 pieces</li> <li>Test date: 17 May 2022</li> </ul>

## Notes:

- a) \*Denotes measurement uncertainty
- b) The reported uncertainty is calculated using a coverage factor k=2, which gives a level of confidence of approximately 95%
- c) \*\*Not SAMM Accredited

